

WOOD

Vintage
Atelier Collection

Product
Datasheet
2015



WOOD

Vintage

Atelier Collection



TECHNICAL INFORMATION	VINTAGE
Thickness	14 mm
Width	162 / 190 mm
Length	2000-2200 mm
Wearlayer thickness (mm)	app. 3,5
Weight (kg/m ²)	app. 8,0
Taber Abraser/Lacquer's wear resistance prEN 13696	
abrasion penetration Proteco Lacq.(revs)	>4000
abrasion penetration Proteco Nat.(revs)	>3500
abrasive wear (mg/100revs)	app. 3,5
<i>Data show results with new components according to 2006 update. Results not applicable for stained, brushed or hardwax oiled products.</i>	
Reduction of sound weighted index index "footfall" to the room below.	
NF EN ISO 140-8 / Acc to NF EN ISO 717-2, ΔL _w in dB with 2 mm Tarkofoam/flex II	17
Formaldehyde emission EN 13986	E1
Reaction to Fire EN 13501	D _{fl}
Thermal insulation value (RT m ² K/W)	
board only	0,101
with rag felt	0,121
with 2 mm Tarkofoam/flex II	0,141
Installation*	Floating / Glue down
Underfloor heating compatible**	Maximum floor surface temperature 27°C with self-regulating under-floor heat system.

* Contact your flooring supplier for further information.

** Not suitable for the woodspecies beech and maple.

Vintage Proteco Natura

TARKETT SUSTAINABILITY TAG	97 % 97 % Natural Renewable	100 % Recyclable
----------------------------	--------------------------------------	---------------------

Vintage Proteco Hardwax Oil

TARKETT SUSTAINABILITY TAG	98 % 98 % Natural Renewable	100 % Recyclable
----------------------------	--------------------------------------	---------------------

Wood floors, Brinell Hardness (BHN), EN1534

