


## Specification

Modular vinyl floorcovering, with glass fibre reinforcement. Topclean XP™ polyurethane reinforcement.  
In plank form, with beveled edges.  
Product standard: ISO 10582 - EN 649.

CERTIFICATION & CLASSIFICATION	STANDARDS	ID INSPIRATION CLICK
Type of floor covering	EN 649 - ISO 10582	Compact Resilient Floorcovering
CE certification	-	Yes
Class of use	EN 685 - ISO 10874	Commercial: 33 Industrial: 42
TECHNICAL CHARACTERISTICS	STANDARDS	ID INSPIRATION CLICK
Overall thickness	EN 428 - ISO 24346	5.0 mm
Wear layer thickness	EN 429 - ISO 24340	0.55 mm
Surface treatment (PUR / Extreme)	-	Yes
Beveled edges	-	Yes
Total weight	EN 430 - ISO 23997	8,300 g/m <sup>2</sup>
Abrasion group	EN 660-2	Group T: ≤ 2.00 mm <sup>3</sup>
Dimensions	EN 427 - ISO 24342	18.5 x 121.2 cm
Packaging	-	8 planks / box (= 1.793 m <sup>2</sup> - 15.25 kg) - 64 boxes /pallet (= 114.752 m <sup>2</sup> - 991 kg)
TECHNICAL PERFORMANCES	STANDARDS	ID INSPIRATION CLICK
Dimensional stability	EN 434 - ISO 23999	0.10%
Reaction to fire	EN 13501-1	Cfl-S1 Bfl-S1 when using Tarkomfort PRO
Residual indentation	EN 24343-1	0,07 mm
Furniture leg	EN 424	No damage
Castor chair	EN 425 - ISO 4918	Type W
Curl resultant to heat	EN 434 - ISO 23999	≤ 2 mm
Impact sound reduction	EN 140-8	7 dB 13 dB when using Tarkomfort PRO
Underfloor heating	-	Suitable - max. 27°C
Thermal resistance	EN 12667	0,03 (m <sup>2</sup> K)/W
Light fastness	EN ISO 105-B02	≥ 6
Resistance to chemicals	EN 423	Resistance
Slip resistance	EN 13893 DIN 51130	μ ≥ 0,30 DS R9
Antistatic properties	DIN EN 181	< 2 kV

Technical data in force upon the date of publication (05/14). The values correspond to laboratory tests (no in situ test) and are subject to modification. Tarkett's instructions regarding installation, cleaning and maintenance shall be observed. Please contact your local sales rep. for these instructions.



\*Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)